

## Conference Paper

# Ways for Recycling of Quartz Waste in the Production of Silicate Materials

Irina Pavlova, Kirill Zemlyanoi, Elena Farafontova, and Galina Girenko

Federal State Autonomous Educational Institution of Higher Education «Ural Federal University named after the first President of Russia B.N.Yeltsin», Ekaterinburg, Russia

## Abstract

The technological properties of quartz waste associated with the clay deposit are investigated by way of emission spectral analysis, petrography and X-ray phase analysis. This study considers the possibility of quartz waste utilization in the production of dry building mixtures as a filler, magnesia-quartz proppants as a raw material component, cement as a siliceous component, fine ceramics as a partially fluxing and exhausting component, silicate brick as the main raw material. In the production of glass and glassware it is possible to make use of the quartz waste as a glass-forming component including silicate blocks after refining for the  $Al_2O_3$  and  $Fe_2O_3$  content. Quartz waste can be recommended as molding sand after refining for the contents of  $Fe_2O_3$ ,  $Na_2O$ ,  $K_2O$ ,  $MgO$ ,  $CaO$ . Improvement of the properties of the quartz waste can be achieved by ways of elutriation to remove the clay component as well as magnetic separation to remove magnetic compounds of iron.

Corresponding Author:

Irina Pavlova

i.a.pavlova@urfu.ru

Published: 31 December 2020

Publishing services provided by  
Knowledge E

© Irina Pavlova et al. This article is distributed under the terms of the [Creative Commons Attribution License](#), which permits unrestricted use and redistribution provided that the original author and source are credited.

Selection and Peer-review under the responsibility of the TECHNOGEN-2019 Conference Committee.

**Keywords:** quartz waste, proppants, glass, cement, silicate brick, building mixtures, fine ceramics, molding sand, recycling

## 1. Introduction

Given the current state of consumption of natural raw materials, the utilization and involvement of secondary material resources in social production is significant. The integrated use of raw materials and waste is also associated with solving the problem of non-waste and environmentally friendly technologies creation [1]. A special interest is the use of technogenic raw materials which, on the one hand, ensures the saving of natural raw materials and, on the other hand, allows it to be disposed of improving the environmental situation [2, 3]. To use local raw materials, it is necessary to develop new effective technologies or improve existing methods to produce silicate materials [1]. This article deals with the utilization of quartz waste after extraction of titanium-containing components.

From the geological point of view the quartz sand is a sedimentary fine-grained, non-cemented rock consisting of mineral grains of 0.005–2.0 mm in size. Quartz sand is a conglomerate, sedimentary rock, comprising mainly by quartz grains [4].

## OPEN ACCESS

There are clay deposits on the territory of Tyumen region (Russia). The potential of this raw material has not been sufficiently studied for the construction industry [5, 6]. The aim of this work is to study the possibility of using quartz waste of raw materials after extraction of titanium-containing components to obtain dry building mixtures, proppants, cement and silicate brick, glass and glassware, fine ceramics and its use as molding sand.

## 2. Experimental Procedure

The chemical composition of quartz waste was determined by emission spectral analysis with inductively coupled plasma using Optima 4300 DV optical emission spectrometer (Perkin Elmer, USA). The grain composition, modulus of sand fineness and true density using the pycnometric method were determined in accordance with [7]. Petrographic studies of refractory products were carried out in reflected light by optical microscope Polam R-311.

## 3. Results and Discussion

This paper presents the experimental results of possible utilization of quartz waste depositing in Tyumen region (Russia) in the production of silicate materials.

The suitability of quartz waste for construction work was examined accordance with [8]. The grain composition and modulus of sand fineness determined in accordance with [7] are presented in Table 1 (Author's own work).

TABLE 1: Grain composition of quartz waste.

Sieve residue	Fraction content, mass %, mm							
	2.5	1.25	0.63	0.315	0.16	0.1	0.004	0
partial	3.5	2.0	1.5	1.2	12.1	67.47	11.97	0.26
full	3.5	5.5	7	8.2	20.3	87.77	99.74	100

The full residue on sieve No. 063 is 7% (see Table 1) which corresponds to a very fine sand. Quartz waste visually contains large pieces (more than 5 mm). When sifted these pieces are easily destroyed and the entire sample of quartz waste passes through a No. 5 sieve, i.e. this quartz waste does not contain particles larger than 5 mm. A particle content of less than 0.16 mm is 79.7% which allows quartz waste to be classified as very fine sand. The class of quartz waste corresponds to II with a particle size modulus of 0.44 [8].

The clay content in the quartz waste clots is 5% and for fine and very fine sands should not exceed 1%. The content of dusty and clay particles in the quartz waste is 5.6% which is in agreement with [8] (up to 10%).

Due to the presence of organic impurities the quartz waste is suitable for use in concrete and mortars since the liquid above quartz waste sample has been slightly colored. The optical density of the liquid above the waste is 0.044 compared to a standard solution with an optical density of 0.6–0.68.

The true density of quartz waste determined by the pycnometric method [7] is  $2647 \text{ kg}\cdot\text{m}^{-3}$ . The bulk density of waste is  $1339 \text{ kg}\cdot\text{m}^{-3}$ , the voidness is 49.4% and the absolute humidity is 0.5%.

The reactivity of quartz waste is 37.24 mmol/l which meets the requirements of [8] (not more than 50 mmol/l). The quartz waste contains a permissible amount of amorphous varieties of silicon dioxide soluble in alkalis (chalcedony, opal, flint, etc.). Quartz waste can be used as filler for concrete due to its resistance to the chemical effects of alkali cement.

The sulfide sulfur content in the quartz waste is 0.0043% and the sulfate sulfur one is 0.015%. According to [8] sulfur, sulfides, except pyrite (marcasite, pyrrhotite, etc.) and sulfates (gypsum, anhydrite, etc.) in terms of  $\text{SO}_3$  should be no more than 1.0%, pyrite in terms of  $\text{SO}_3$  not more than 4% by weight. Therefore, the quartz waste under investigation is suitable for use as filler for concrete and mortar.

For the suitability of the quartz waste in road construction the content of clay particles by the swelling method was determined [8]. The increment of the material volume in the quartz waste was not observed. The quartz waste under study can be used in road construction.

Thus, quartz waste can be used as filler of heavy, light, fine-grained, cellular and silicate concrete, mortar, production of dry mixes as well as for the construction of bases and coatings of roads and airfields after removing clay in clots by elutriation or dry sieving way.

For the utilization of quartz waste in proppant production the chemical composition and particle size distribution of waste are determined [9, 10]. The chemical composition of quartz waste is presented in Table 2 (Author's own work).

TABLE 2: Chemical composition of quartz waste.

Component	$\text{Al}_2\text{O}_3$	BaO	CaO	$\text{Cr}_2\text{O}_3$	$\text{Fe}_2\text{O}_3$	$\text{K}_2\text{O}$	MgO	$\text{Mn}_2\text{O}_3$	$\text{Na}_2\text{O}$	$\text{SiO}_2$	$\text{TiO}_2$
Weight content, %	4.274	0.0541	0.239	0.014	1.179	2.075	0.107	0.0437	0.679	88.181	1.122

According to [9] the MgO content should be at least 8%. The MgO content in waste is 0.107% (see Table 2) which does not meet the requirements of the state standard. According to [10] the  $\text{Al}_2\text{O}_3$  content should be at least 50%. In the waste it is 4.274% which also is out of line the requirements. In addition, the minimum size of proppants defined by standards is 0.212 mm. The waste in the bulk (80–90%) consists of particles with a size not exceeding 0.16 mm. Thus, quartz waste can be used as a raw silica-containing component to produce proppants.

The possibility of using quartz waste as molding sand in foundry is investigated. According to [11] the content of silicon dioxide should be at least 90.0% and the content of  $\text{SiO}_2$  in the waste is 88.181% (see Table 2) which does not correspond to the required characteristics. In addition, the content of harmful impurities  $\text{Fe}_2\text{O}_3$  in the waste is 1.179% and according to GOST it should be no more than 1%. The total content of  $\text{Na}_2\text{O}+\text{K}_2\text{O}+\text{MgO}+\text{CaO}$  is 3.1% and according to GOST it should not be in excess of more than 2%.

Thus, the quartz waste does not meet the requirements of the state standard in terms of chemical composition and cannot be recommended for use as molding sand due to the higher content of fluxing oxides.

State standards defining the requirements for sand to produce silicate brick and cement do not exist. Until 2002 there was an industry standard [12] which presented the following requirements for sand: particle size modulus is up to 2, moisture content is up to 8%, dust content, clay, clay mud is not more than 10%, the content of organic impurities is not darker than the color of the standard, the average density is not less than  $1200 \text{ kg}\cdot\text{m}^{-3}$ , the content of quartz (unbound  $\text{SiO}_2$ ) is not less than 50%.

The particle size modulus of quartz waste is 0.44, the content of dusty, clay and clay impurities is 5.46%, humidity is 0.5%, the quartz content determined according to [13] is 86.9% which corresponds to industry standard requirements.

To produce silicate brick, the mountain and ravine sands consisting of sand grains of an acute-angled shape with a rough surface which contributes to their good adhesion to lime are desirable. River and lake sands containing rounded sand grains with a smooth surface do not adhere well to lime [14]. Petrographic studies of quartz waste showed that grains have a predominantly rounded shape.

Due to its high dispersion and clay components content the quartz waste can be claimed as a siliceous type of raw material to produce Portland cement.

To study the possibility of using quartz waste in the production of glass and glassware, [15] is used. It was established that the quartz waste does not meet the standard requirements for the T brand to produce bottle green and dark green glass in chemical composition:  $\text{Al}_2\text{O}_3$  content is 4.274%, and the content  $\text{SiO}_2$  is 88.181%. According to

GOST content should be up to 4.0% and not less than 95% respectively. For all other grades the waste does not meet the requirements [15] for the  $\text{Fe}_2\text{O}_3$  content. The content of iron oxide is 1.179% (see Table 2) by contrast to the requirements of GOST (up to than 0.25%).

To produce silicate blocks, the quartz sands of grade B-100-1 are used [15]. The chemical composition of sand should meet the following requirements:  $\text{Al}_2\text{O}_3$  content is not more than 0.6%,  $\text{Fe}_2\text{O}_3$  content is up to 0.1%,  $\text{SiO}_2$  content is not less than 98.5%. On account of all three indicators the quartz waste does not meet the specified requirements.

By grain composition the fraction content of less than 0.1 mm should be no more than 10% for unenriched sands. The quartz waste under study contains 12.25% fractions of less than 0.1 mm (see Table 1).

Thus, quartz waste can be used in the glass industry including the production of silicate blocks after appropriate refinement in the content of  $\text{SiO}_2$ ,  $\text{Al}_2\text{O}_3$  and  $\text{Fe}_2\text{O}_3$  and removal of the fraction of less than 0.1 mm.

The possibility of using quartz waste in the production of fine ceramics is determined. According to [16] the sand does not comply with the following indicators:  $\text{SiO}_2$  content should be not less than 93%, the total content of  $\text{Fe}_2\text{O}_3 + \text{TiO}_2$  should be not more than 0.3%. In the waste sample they are 88.181% and 2.31% respectively.

Petrographic studies showed that the source clay contains hydromica (muscovite and biotite) in an amount of 10–15%. To produce ceramic tiles, in particular for the internal wall cladding and for floor tiles the clay, alkali-containing components (meshes) and sands are always introduced into the mass composition. Therefore, the studied quartz waste can be claimed by manufacturers of ceramic tiles including porcelain.

## 4. Conclusion

The principal possibility of obtaining silicate materials based on quartz waste remaining after extraction of titanium-containing components from raw materials is shown. The basic technological properties of quartz waste were studied. The parameters were examined for compliance with the requirements of state standards used in the production of silicate materials.

The quartz waste under study can be recommended as a filler for heavy, light, fine-grained, cellular and silicate concrete, mortar, and preparation of dry mixes. The quartz waste can be claimed as a raw material component to produce ceramic tiles including porcelain stoneware as well as proppants. Quartz waste can be used in the glass

industry including in the production of silicate block after appropriate refinement in the content of  $\text{Al}_2\text{O}_3$  and  $\text{Fe}_2\text{O}_3$  and removal of fractions less than 0.1 mm.

## References

- [1] Ramdani, S., *et al.* (2019). Physical and Mechanical Performance of Concrete Made With Waste Rubber Aggregate, Glass Powder and Silica Sand Powder. *Journal of Building Engineering*, vol. 21, pp. 302-311.
- [2] Kazanskaya, L. F. and Smirnova, O. (2018). Supersulphated Cements with Technogenic Raw Materials. *International Journal of Civil Engineering and Technology*, vol. 9, issue 11, pp. 3006-3012.
- [3] Yatsenko, N. D., *et al.* (1999). An Efficient Technology for Production of Faience Articles using Calcium-Containing Waste. *Glass and Ceramics*, vol. 56, pp. 271–273.
- [4] Magenheimer, S. and Mazzullo, J. (1987). The Original Shapes of Quartz Sand Grains. *Journal of Sedimentary Petrology*, vol. 57, issue 3, pp. 479-487.
- [5] Kapustin, F. L. and Shul'meister, T. M. (2017). Keramdor Production Based on Tyumen Clays. *Glass and Ceramics*. vol. 73, pp. 3-4.
- [6] Pavlova, I. A., *et al.* (2016). Tyumen Clays in the Production of Building Ceramic. *Glass and Ceramics*. vol. 72, pp. 341-344.
- [7] GOST 8735-88. Sand for Construction Work. Testing methods. Moscow: Standartinform.
- [8] GOST 8736-2014. Sand for Construction Works. Specifications. Moscow: Standartinform.
- [9] GOST R 54571-2011. Magnesial-quartz proppants. Specifications. Moscow: Standartinform.
- [10] GOST R 51761-2013. Aluminosilicate proppants. Specifications. Moscow: Standartinform.
- [11] GOST 2138-91. Moulding sands. General specifications. Moscow: Standartinform.
- [12] OST 21-1-80. Sand for the Production of Autoclaved Silicate Products. Moscow: Izdatel'stvo Standartov.
- [13] GOST 21216-2014. Clay Raw Materials. Test methods. Moscow: Standartinform.
- [14] Gilchrist, J. D. (1977). Silica Bricks. In *Fuels, Furnaces and Refractories*. Oxford: Pergamon Press, pp. 273-283.
- [15] GOST 22551-77. Quartz Sand, Ground Sandstone, Quartzite and Veiny Quartz for Glass Industry. Specifications. Moscow: IPK Izdatel'stvo Standartov.

- [16] GOST 7031-75. Quartz Sand for Fine Ceramics. Moscow: State Committee of Standards of the Council of Ministers of the USSR.